

GLYCELANE

DEFINITION	GLYCELANE is a matt finish water-based microporous decoration paint for façades.D2 class. GLYCELANE has been formulated on a basis of a mixing of acrylic and siloxan bindings. GLYCELANE assures the protection and decoration of outdoor masonries exposed to atmospheric pollution and to the dirtying.
PROPERTIES	<ul style="list-style-type: none"> - Good impermeability to rain waters. - Excellent permeability to water vapour. - Beading effet: reduce atmsopheric dirtying - Excellent performance on alkaline substrates. - Good resistance of the colours to ultraviolet. - Mineral matt finishing aspect. - Rapid drying. - High spreading rate.
SUBSTRATES	All cement traditional not structured masonries (cement rendering, concrete, facing bricks), old inorganic or organic adhering matt decorative thin paint.
TECHNICAL DATAS	
Classification V.O.C.	AFNOR NFT 36005 – Family I – Class 7b2/10c E.U. limit value of this product (Cat. A/c) : 40 g/l (2010). This product contains max. 30 g/l.
Composition	Aqueous dispersion of maxed acrylic and siloxan bindings
Density	1.34 kg/l
Non volatile matter	53%
Flash point	Not flammable
Aspect	Deep matt
Colour	White. Pastel colours obtained with 1% max. of solvent free universal dyestuffs.
Drying at 20°C	Dust proof : 30 min - Recoatable: 3 to 4 hours (allow for adequate ventilation during the drying period).
Spreading rate	10 to 14 sqm/l per coat on smooth surfaces.
Dilution	Ready for use.
Gloss at 60°	< 2
USE ADVICES	
Substrates' preparation	In all cases, dirt and non-adhering particles have to be eliminated with a high-pressure machine or by a scrubbing.
Application conditions	GLYCELANE can be applied with a brush, a roller or a pulverizer on a prepared clean and dry substrate according to the NF P 74-201-1 standard (D.T.U 59.1). The substrate must be dry with superficial temperature of between +5°C and +35°C. Do not apply when the relative humidity is above 80% during application. On porous substrate, on powdery or irregular substrate, prime with CELOPRIM . Apply 2 coats of GLYCELANE .
Cleaning	Wash with clean water immediately after use.
SHELF LIFE	2 years starting from the manufacturing date, in unopened packing of origin stored in frost-free conditions.
PACKAGING	15 L pails.
HYGIENE AND SAFETY	SDS available on websites www.artilin.fr or www.quickfds.com

