

GLYCELO PLAFOND

GLYCELO CEILING

DEFINITION	GLYCELO PLAFOND is an insulating matt finish water based paint, especially developed to obtain an excellent finishing on interior ceilings and walls. Particularly recommended for ceilings as an alternative to the use of solvent based paints.
PROPERTIES	<ul style="list-style-type: none"> - Ready for use. - Insulating of smoke and nicotine black stains and water rings, directly in 2 coats. - Water based : user-friendliness and easy to apply. - Allows a well finish without overlaps. - Rust-proofing additive (head of screws...). - Does not run or splash when applied. - Does not create any surface tension on old matt finish adhering paint. - Excellent matity and whiteness. - Slight odour, ideal for the renovation of occupied premises. - Low rate of V.O.C.
SUBSTRATES	Rough plaster, cleaned whitewash or old adhering matt paint, polystyrene mouldings. Other substrates : as finishing coat on gypsum boards.
TECHNICAL DATAS	
Classification	AFNOR NF T 36005 – Family I–Class 2b
Composition	Acrylic aqueous dispersion, titanium dioxide.
V.O.C.	E.U. limit value of the product (Cat. A/a) : 75 g/l (2007) / 30 g/l (2010). This product contains max. : 4 g/l
Density	1.44 kg/l
Non volatile matter	62%
Flash point	Not flammable
Aspect	Deep and tight matt.
Colour	White. Pastel colours obtained with 2% max. solvent free universal dyestuffs.
Drying at 20°C	Touch dry : 1 h - Recoatable : 6 h on non stained substrates or 12 h on stained substrates in order to obtain a good insulating power (indicated values given for well ventilated room).
Spreading rate	8 to 11 sqm/l per coat according to substrate porosity and relief.
Dilution	Ready for use. Do not dilute. A too important dilution can affect the insulating power on stained substrates.
Gloss at 60°	1 to 2
Gloss at 85°	About 1
USE ADVICES	
Application conditions	GLYCELO PLAFOND can be applied with a brush, a roller or a spray gun on a dry, clean, degreased and adhering substrate in accordance with NF P 74-201-1 standard (D.T.U 59.1). Do not apply with temperatures under 8°C or with high hygrometry rate. Apply two coats of GLYCELO PLAFOND in order to obtain the insulating power on stains. In case of very much stained substrates, cover over the stains with GLYCELO PLAFOND and then apply 2 coats. On new gypsum boards on ceilings, apply first a coat of GLYCELO MAT and the one finishing coat of GLYCELO PLAFOND .
Cleaning	Wash with clean water immediately after use.
STORAGE	Store in frost-free conditions.
PACKAGING	15 L tins and cardboardboxes of 4 x 2,5 L tins.
HYGIENE AND SAFETY	<i>SDS available on websites www.artilin.fr or www.quickfds.com</i>

REMARK :

As we do not know in which conditions our products are used, our responsibility cannot be engaged when the instructions here above indicated are not respected, being based upon test results carried out in our laboratories.



B.P. 12 - 47450 COLAYRAC-SAINT-CIRQ - FRANCE
Tél : +33(0)5.53.87.51.65. - Fax : +33(0)5.53.676.676
E-mail : artilin@artilin.fr