

GLYCELO VELOUTE

GLYCELO CREAMY SEMI-GLOSS

DEFINITION

GLYCELO VELOUTE is a semi-gloss finish water based paint with a very high coverage, based with alkyd resins in emulsion, specially developed to obtain an excellent finishing on interior walls and ceilings made of gypsum boards.

Two coats of **GLYCELO VELOUTE** are enough to cover the base of gypsum boards, the coating over the joints and the fixing holes.

GLYCELO VELOUTE can also be applied on exterior.

PROPERTIES

- Ready for use.
- **Outstanding opacity : apply GLYCELO VELOUTE directly on the gypsum board. It is not necessary to apply a primer before painting with GLYCELO VELOUTE.**
- Excellent filling and covering properties
- Does not run or splash when applied.
- Very pleasant to apply because of its slight odour.

SUBSTRATES

Gypsum board on interior walls and ceilings.

Other substrates : glass textile wall covering, wooden panels, extruded polystyrene, cement coating, brick, cinder block, old adhering matt finish paints, plaster and by-products, cellular concrete, wood.

TECHNICAL DATAS

Classification V.O.C.

AFNOR NF T 36005 Family I-Class 7a2

E.U. limit value of this product (Cat. A/a) : 75 g/l (2007) / 30 g/l (2010).

This product contains max. 17 g/l.

Composition

Mixed vinyl-alkyd aqueous dispersion.

Density

1.6 kg/l

Non volatile matter

68 %

Flash point

Not flammable

Aspect

Semi-gloss matt

Colour

White. Pastel colours obtained with 2% max. of solvent free universal dyestuffs.

Drying at 20°C

Touch dry : 1 hour – Recoatable : 6 hours

(Allow for adequate ventilation during the drying period).

Spreading rate

8 to 11 sqm/l by coat according to substrate porosity and relief (i.e. 140 to 200 g/sqm).

Respect this quantity : higher quantities applied with the airless spray would cause some aspect defects.

Gloss at 60°

2

Gloss at 85°

35

USE ADVICES

Application conditions

Apply **GLYCELO VELOUTE** with paint brush, conventional roller or spray gun (use preferably 519 or 619 nozzles). Remove oil, grease or any other contaminants and apply **GLYCELO VELOUTE** on a prepared, clean and dry substrate in accordance with NFP 74-201-1 standard (DTU 59.1.).

Do not apply when substrate temperatures are likely to fall below 8°C or when the relative humidity is above 80% during application or the drying period. Ready for use for the gypsum board. If applied on old bases, on wood or with airless spray-gun dilute with water if necessary (3% maximum).

On old bases still powdery after preparation, apply **GLYCEPRIM FONGICIDE** to fix the base.

On plaster and plaster blocks, dilute the first coat between 5 and 10%.

Apply two coats of **GLYCELO VELOUTE** to obtain a perfect opacity.

Cleaning

Wash with clean water immediately after use.

STORAGE

Store in frost-free conditions.

PACKAGING

15 L tins and cardboard boxes of 4 x 2.5 L tins.

HYGIENE AND SAFETY

SDS available on websites www.artilin.fr or www.quickfds.com

REMARK :

As we do not know in which conditions our products are used, our responsibility cannot be engaged when the instructions here above indicated are not respected, being based upon test results carried out in our laboratories.



B.P. 12 - 47450 COLAYRAC-SAINT-CIRQ - FRANCE
Tél : +33(0)5.53.87.51.65. - Fax : +33(0)5.53.676.676
E-mail : artilin@artilin.fr